

GlucoStar[®] C65

GlucoStar[®] C65 is a cold-water soluble, low viscosity, carboxymethyl polymer for use in industrial applications. It provides fermentation and enzyme resistance without the addition of preservatives. GlucoStar C65 offers a unique alternative to competitive natural and synthetic water-soluble polymers.

The low viscosity and high solubility of GlucoStar C65 make it particularly suited for use as a binder in high solids adhesive formulations. Its highly anionic character promotes flocculation of positively charged materials and the polymer is an excellent candidate where binding and adhesion is desired without viscosity.


Application Properties

- Flocculation
- Lubrication
- Adhesion
- Suspension
- Fermentation Resistance
- Colloid Protection
- Film Formation
- Binding
- Water Retention

Appearance

GlucoStar C65 is an off- white powder. Aqueous solutions are translucent and demonstrate excellent stability.

Solids vs. Viscosity Curve



Solution Preparation

GlucoStar C65 readily solubilizes in water. Preparation of aqueous solutions requires the addition of GlucoStar C65 to the vortex of mechanically agitated water at ambient temperature. Maintain agitation for a period of about 20 minutes to ensure separation and complete hydration of individual particles. Any agglomerates that initially form will break down with normal agitation and time.

The character and amount of agitation required will vary with solids concentration of the polymer and water temperature. High solids and cold water make-up may necessitate longer agitation time.

Hydration

GlucoStar C65 exhibits a rapid hydration profile, providing short mixing times necessary to fully solubilize the polymer.

Solution Preservation

The chemical modification of GlucoStar C65 provides enhanced solution bio-stability. This feature provides an advantage where biocides cannot be used.

Storage, Handling and Safety

Because of the hygroscopic nature of GlucoStar C65, it is highly recommended that the material be stored in its original package in a dry facility. Shelf life can be affected by storage conditions such as temperature, humidity and overall surroundings of the storage area. A Safety Data Sheet is available from Chemstar and should be consulted prior to handling or use.

Availability

GlucoStar C65 is available in 50 lb multi- wall poly-lined paper bags and 2,000 lb super sacks for truckload and LTL shipments. For additional information, samples or technical assistance in using GlucoStar C65 or any other Chemstar product please contact 1-800-328-5037 or info@chemstar.com



Typical Analysis

GlucoStar C65	
Viscosity (cP), 5% Solids LVT, 60 rpm, #3 Spindle	150 – 550
pH (5% Solids)	9.0 – 10.8
Moisture (%)	10 max
Bulk Density (lb/ft ³)	30 – 45
Particle Size (% thru)	100 (-) 850 micron
Ionic Character	Highly Anionic

Disclaimer: The information contained in this bulletin is correct to the best of Chemstar's knowledge and is intended only as a source of information. The recommendations or suggestions herein are made without guarantee or representation as to the results. In addition, Chemstar suggests that you evaluate the recommendations contained in this bulletin in your own laboratory prior to use. Chemstar's responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material. No statement in this bulletin is to be construed as violating any copyright or patent.

